

ERRATA

AWS B2.1-8-005:2002, Standard Welding Procedure Specification (SWPS) for Gas Metal Arc Welding (Short Circuiting Transfer Mode) of Austenitic Stainless Steel (M-8, P-8, or S-8), 18 through 10 Gauge, in the As-Welded Condition, with or without Backing

The following correction is for an error found in AWS B2.1-8-005:2002, *Standard Welding Procedure Specification (SWPS) for Gas Metal Arc Welding (Short Circuiting Transfer Mode) of Austenitic Stainless Steel (M-8, P-8, or S-8), 18 through 10 Gauge, in the As-Welded Condition, with or without Backing*

Page 3, Electrical Characteristics Table, under "Volts" column heading, change all entries as follows:

"70-90"	to	"16-19"
"76-94"	to	"16-19"
"82-99"	to	"16-19"
"88-103"	to	"16-19"
"94-108"	to	"17-20"
"100-112"	to	"17-20"
"106-117"	to	"17-20"
"113-121"	to	"17-20"
"120-125"	to	"17-20"