Research led to the development of a nitrogen- and manganese-modified, high-nickel stainless steel alloy for a demanding cryogenic magnet application

BY S. F. KANE, A. L. FARLAND, T. A. SIEWERT AND C. N. McCOWAN

ABSTRACT. This paper summarizes the development and qualification of an appropriate welding consumable for a demanding cryogenic magnet application. It begins with a review of the research conducted on cryogenic fracture toughness of wrought and welded austenitic stainless steels. This research shows that certain elements of the composition have a powerful effect upon the steel's fracture toughness at 4 K. In particular, the higher oxygen content in the weld manifests itself as inclusions, which have a severe detrimental effect upon the fracture toughness. This one factor accounts for most of the difference in toughness between wrought and weld materials of similar composition, and is a function of the weld process. Also, welds enriched with manganese and nickel have demonstrated improved fracture toughness. These discoveries were combined in the development of a nitrogen- and manganese-modified, high-nickel stainless-steel alloy. It produced gas metal arc welds with superior cryogenic mechanical properties (yield strength near 900 MPa at 4 K and a Charpy V-notch impact energy near 140 J at 76 K) when the procedures were modified to reduce the oxygen content.

Background

In 1983 and in 1989, the nuclear physics community prepared long range plans for the U.S. Department of Energy and the National Science Foundation. In both years, they identified the Relativistic Heavy Ion Collider (RHIC) as the highest priority for facility construction. In response, the U.S. Congress appropriated the first construction funds for the RHIC

S. F. KANE and A. L. Farland are with Brookhaven National Laboratory, Upton, N.Y., and T. A. SIEWERT and C. N. McCOWAN are with National Institute of Standards and Technology, Boulder, Colo.

in fiscal year 1991. The construction of the RHIC, at the Brookhaven National Laboratory (BNL), will provide the United States with a world-class facility with a potential for unique discoveries. Specifically, the RHIC will be able to create matter at extremely high temperatures and densities — so extreme that scientists hope to observe phenomena that have not occurred in the natural universe since the original "Big Bang." These experiments cannot be conducted at existing high-energy accelerator facilities.

In the RHIC, two beams of heavy ions will speed in opposite directions inside a pair of rings in a tunnel almost 3.9 km in circumference. The beams will be bent and focused by more than 1700 superconducting magnets. The material and magnetic property requirements (material strength to resist the mechanical loads and the fracture toughness requirements at 4 K) of these magnets are very demanding. This paper concentrates on the weld design and materials to meet the design requirements of the superconducting magnet structures.

BNL Magnet Design Requirements

A superconducting magnet has the same basic structure as a traditional electromagnet — an iron core wound with an

electrical cable. In the case of niobium-titan superconducting magnets, the electrical cable is superconducting and must be maintained at a temperature of less than 4.6 K. The cable and iron core are enclosed within a cryogenic pressure vessel to provide this cooling. The U.S. Department of Energy requires that all pressure vessels at its facilities comply with the American Society of Mechanical Engineers (ASME) *Boiler and Pressure Vessel Code*. These requirements, coupled with the cryogenic system design and manufacturing cost parameters, require a weld yield strength of 900 MPa for the 4.8-mm-thick stainless steel magnet shells, a ferrite number (FN) less than 3 for weld processes other than gas tungsten arc welding (GTAW) and gas metal arc welding (GMAW) and a lateral expansion greater than 0.38 mm for a Charpy V-notch (CVN) impact test at the operating temperature. ASME Code paragraph UG-84 requires impact testing for applications operating at temperatures below 19 K, where the RHIC pressure vessels will be operating, yet impact testing at 4 K is complicated by the low heat capacity of materials at this temperature. The ASME Code (originally developed for applications near room temperature or above) had been applied to cryogenic temperatures without adjusting for the changes in the physics of heat flow and deformation. The standard Charpy impact test prescribed by the American Society for Testing and Materials (ASTM) Standard E 23 becomes questionable at extreme cryogenic temperatures. Recent studies show that a specimen cannot be transferred from a 4 K cooling bath to the test machine quick enough to avoid exceeding the test temperature by a large margin (Ref. 1). Furthermore, the adiabatic heating associated with deformation has such an influence on all materials at this temperature that the deformation preceding fracture often in-

KEY WORDS

Cryogenic
Ferrite
Fracture Toughness
Gas Metal Arc Welding
Inclusions
Nitrogen
Stainless Steel
Strength

Fig. 7 — CVN impact energy.

Fig. 8 — CVN lateral expansion.

creases by a factor of 2.5 when the temperature is decreased to 4 K. Studies also show that increasing the nitrogen from the typical weld nitrogen content of 0.05% to 0.20% yields a threefold increase in strength when cooled to 4 K.

Nitrogen cannot be added without limit. The upper limit is determined by the solubility of nitrogen in the microstructure. Weld porosity occurs above this limit. The solubility limit is a function of the composition, with certain elements (such as manganese) serving to increase the limit (Ref. 8). Manganese at a concentration above the 1.5 wt-% typical for austenitic stainless steels was added to provide greater protection from porosity formation and to act as a solid solution strengthener.

Nickel

Nickel also has a significant, though nonlinear, effect on toughness. Figure 3 shows that increasing nickel from 10 to 20% in the welds provides the greatest improvement in toughness. Thus, a weld with more than 20% nickel should exhibit the greatest attainable toughness for an austenitic stainless steel. Workers at NIST performed work to determine an optimum weld material for 316LN, which is a popular base material for demanding cryogenic applications (Ref. 7). Two commercially available compositions (18Cr-20Ni-5Mn-0.16N and 20Cr-25Ni-4.5Mo) were evaluated using GMAW. Shielding gases were more inert than normal to reduce oxygen content, and the gas used for the 20Cr-25Ni-4.5Mo electrode was augmented with nitrogen to increase the nitrogen content of the weld metal. Figure 4 shows the strength was comparable to that of 316LN base metal and the fracture

toughness was equal to or greater than that of the 316LN base metal. This toughness clearly exceeds the toughness achievable with 308- and 316-based welding compositions and standard welding procedures.

Other research shows that higher nickel contents improve the toughness in two ways: nickel reduces the ferrite content of the weld metal (a magnetic microstructural phase and more brittle than austenite), and nickel additions increase the toughness in fully austenitic compositions (Refs. 9-12). Figure 3 shows how additions of nickel to stainless steel alloys generally increase the toughness, at least up to 20 wt-%. A secondary benefit is that nickel stabilizes austenitic structures against the formation of martensite (another magnetic phase) during deformation. The two references on the fabrication of the cryogenic magnet structures mentioned their search for these magnetic phases during qualification and control of the welding procedure (Refs. 3, 4).

Tramp Elements

Fully austenitic compositions may be subject to hot cracks, which are ruptures that form in the hot weld during solidification. Studies show this tendency can be controlled by careful control of "tramp" elements, phosphorus and sulfur, that produce a low-melting-point eutectic (Ref. 3). This problem is evident in electrode specifications where crack-sensitive compositions can be available in a special grade with stricter limits on the elements that promote hot cracking. Sometimes the fully austenitic grades can be made less sensitive to cracking by adding elements such as manganese, copper or carbon that change the solidification structure. These elements may

change the shape of the solidification front or change the amount of terminal eutectic between adjacent dendrites.

Oxygen

Because of its reactivity, free oxygen is not found in the weld. Instead, it combines with other elements to form oxide inclusions. These inclusions have diameters near 1 μm and are spherical because they form in the liquid above the solidification temperature. As the weld cools, these inclusions are entrained in the solid and have little effect on mechanical properties until the weld is deformed. Inclusions are harder than the surrounding metal matrix and serve as impediments to dislocation motion during deformation. As a result, substantial stresses form in the vicinity of oxide inclusions, causing voids to initiate. These voids then link by void coalescence, leading to final fracture of the material. Since the voids nucleate at inclusions, reduction in the density and size of inclusions reduces the number of voids that form and is an obvious step in increasing the toughness of a weld. Stainless steel welds usually have lower toughness than wrought material. The primary difference between weld material and wrought material is the amounts of inclusions and ferrite. Welds will contain more inclusions because of the imperfect gas shielding of the metal while molten. Studies have shown that correlation of toughness with inclusion spacing is similar for wrought material, which suggests that the differences in fracture toughness can primarily be attributed to this one factor (Refs. 14, 15).

Research on the effects of the welding process and shielding gas on toughness has been conducted using 308, 308L and 316L filler metal; GTAW with 100%